

36.”⁴ Certain martensitic precipitation-hardenable stainless steel is also excluded from the scope of this order. This high-strength, ductile stainless steel product is designated under the Unified Numbering System (UNS) as S45500-grade steel, and contains, by weight, 11 to 13 percent chromium, and 7 to 10 percent nickel. Carbon, manganese, silicon and molybdenum each comprise, by weight, 0.05 percent or less, with phosphorus and sulfur each comprising, by weight, 0.03 percent or less. This steel has copper, niobium, and titanium added to achieve aging, and will exhibit yield strengths as high as 1700 Mpa and ultimate tensile strengths as high as 1750 Mpa after aging, with elongation percentages of 3 percent or less in 50 mm. It is generally provided in thicknesses between 0.635 and 0.787 mm, and in widths of 25.4 mm. This product is most commonly used in the manufacture of television tubes and is currently available under proprietary trade names such as “Durphynox 17.”⁵

Finally, three specialty stainless steels typically used in certain industrial blades and surgical and medical instruments are also excluded from the scope of this order. These include stainless steel strip in coils used in the production of textile cutting tools (*e.g.*, carpet knives).⁶ This steel is similar to AISI grade 420 but containing, by weight, 0.5 to 0.7 percent of molybdenum. The steel also contains, by weight, carbon of between 1.0 and 1.1 percent, sulfur of 0.020 percent or less, and includes between 0.20 and 0.30 percent copper and between 0.20 and 0.50 percent cobalt. This steel is sold under proprietary names such as “GIN4 Mo.” The second excluded stainless steel strip in coils is similar to AISI 420–J2 and contains, by weight, carbon of between 0.62 and 0.70 percent, silicon of between 0.20 and 0.50 percent, manganese of between 0.45 and 0.80 percent, phosphorus of no more than 0.025 percent and sulfur of no more than 0.020 percent. This steel has a carbide density on average of 100 carbide particles per 100 square microns. An example of this product is “GIN5” steel. The third specialty steel has a chemical composition similar to AISI 420 F, with carbon of between 0.37 and 0.43 percent, molybdenum of between 1.15 and 1.35 percent, but lower manganese of between 0.20 and 0.80 percent, phosphorus of no more than 0.025 percent, silicon of between

0.20 and 0.50 percent, and sulfur of no more than 0.020 percent. This product is supplied with a hardness of more than Hv 500 guaranteed after customer processing, and is supplied as, for example, “GIN6”.⁷

Analysis of Comments Received

All issues raised in these reviews are addressed in the “Issues and Decision Memorandum” (“Decision Memo”) from Ronald K. Lorentzen, Acting Director, Office of Policy, Import Administration, to James J. Jochum, Assistant Secretary for Import Administration, dated November 15, 2004, which is hereby adopted by this notice. The issues discussed in the Decision Memo include the likelihood of continuation or recurrence of dumping and the magnitude of the margins likely to prevail if the order were to be revoked. Parties can find a complete discussion of all issues raised in this review and the corresponding recommendations in this public memorandum which is on file in room B–099 of the main Commerce Building.

In addition, a complete version of the Decision Memo can be accessed directly on the Web at <http://ia.ita.doc.gov/frn>, under the heading “November 2004.” The paper copy and electronic version of the Decision Memorandum are identical in content.

Final Results of Reviews

We determine that revocation of the antidumping duty order on SSSC from Italy would be likely to lead to continuation or recurrence of dumping at the following percentage weighted-average percentage margins:

Manufacturers/Exporters/Producers	Weighted Average Margin (percent)
ThyssenKrupp Acciai Speciali Terni, S.A.	11.23
All Others	11.23

This notice also serves as the only reminder to parties subject to administrative protective orders (“APO”) of their responsibility concerning the return or destruction of proprietary information disclosed under APO in accordance with 19 CFR 351.305 of the Department’s regulations. Timely notification of the return or destruction of APO materials or conversion to judicial protective order is hereby requested. Failure to comply with the regulations and terms of an

APO is a violation which is subject to sanction.

We are issuing and publishing the results and notice in accordance with sections 751(c), 752, and 777(i)(1) of the Act.

Dated: November 15, 2004.

James J. Jochum,

Assistant Secretary for Import Administration.

[FR Doc. E4–3280 Filed 11–19–04; 8:45 am]

BILLING CODE 3510–DS–P

DEPARTMENT OF COMMERCE

International Trade Administration

[A–428–825]

Stainless Steel Sheet and Strip in Coils From Germany; Final Results of the Expedited Sunset Review of the Antidumping Duty Order

AGENCY: Import Administration, International Trade Administration, Department of Commerce.

ACTION: Notice of final results of expedited sunset review of the antidumping duty order on stainless steel sheet and strip in coils from Germany.

SUMMARY: On June 1, 2004, the Department of Commerce (“the Department”) initiated a sunset review of the antidumping duty order on stainless steel sheet and strip in coils (“SSSC”) from Germany pursuant to section 751(c) of the Tariff Act of 1930, as amended (“the Act”). On the basis of a notice of intent to participate and an adequate substantive response filed on behalf of domestic interested parties and inadequate responses from respondent interested parties, the Department conducted an expedited (120-day) sunset review. As a result of this sunset review, the Department finds that revocation of the antidumping duty order would be likely to lead to continuation or recurrence of dumping. The dumping margins are identified in the *Final Results of Review* section of this notice.

EFFECTIVE DATE: November 22, 2004.

FOR FURTHER INFORMATION CONTACT: Hilary E. Sadler, Esq., Office of Policy for Import Administration, International Trade Administration, U.S. Department of Commerce, 14th Street & Constitution Avenue, NW., Washington, DC 20230; telephone: (202) 482–4340.

SUPPLEMENTARY INFORMATION:

Background

On June 1, 2004, the Department published the notice of initiation of the

⁴ “Gilphy 36” is a trademark of Imphy, S.A.

⁵ “Durphynox 17” is a trademark of Imphy, S.A.

⁶ This list of uses is illustrative and provided for descriptive purposes only.

⁷ “GIN4 Mo,” “GIN5,” and “GIN6” are the proprietary grades of Hitachi Metals America, Ltd.

sunset review of the antidumping duty order on SSSSC from Germany.¹ On June 16, 2004, the Department received a Notice of Intent to Participate from Nucor Corporation; Allegheny Ludlum Corporation; North American Stainless; the United Steelworkers of America, AFL-CIO; the local 3303 United Auto Workers; and Zanesville Armco Independent Organization, Inc. (collectively "domestic interested parties") within the deadline specified in section 315.218(d)(1)(i) of the Department's regulations. The domestic interested parties claimed interested party status under section 771(9)(C) and (D) of the Act, as domestic manufacturers of SSSSC or certified unions whose workers are engaged in the production of SSSSC in the United States. On July 1, 2004, the Department received a complete substantive response from the domestic interested parties within the deadline specified in section 351.218(d)(3)(i) of the Department's regulations. We did not receive responses from any respondent interested parties to this proceeding. As a result, pursuant to section 751(c)(3)(B) of the Act and section 351.218(e)(1)(ii)(C)(2) of the Department's regulations, the Department determined to conduct an expedited review of this order.

Scope of the Order

For purposes of this review, the products covered are certain stainless steel sheet and strip in coils. Stainless steel is an alloy steel containing, by weight, 1.2 percent or less of carbon and 10.5 percent or more of chromium, with or without other elements. The subject sheet and strip is a flat-rolled product in coils that is greater than 9.5 mm in width and less than 4.75 mm in thickness, and that is annealed or otherwise heat treated and pickled or otherwise descaled. The subject sheet and strip may also be further processed (e.g., cold-rolled, polished, aluminized, coated, etc.) provided that it maintains the specific dimensions of sheet and strip following such processing. The merchandise subject to this order is currently classifiable in the Harmonized Tariff Schedule of the United States ("HTS") at subheadings: 7219.13.0031, 7219.13.0051, 7219.13.0071, 7219.1300.81², 7219.14.0030, 7219.14.0065, 7219.14.0090, 7219.32.0005, 7219.32.0020, 7219.32.0025, 7219.32.0035,

7219.32.0036, 7219.32.0038, 7219.32.0042, 7219.32.0044, 7219.33.0005, 7219.33.0020, 7219.33.0025, 7219.33.0035, 7219.33.0036, 7219.33.0038, 7219.33.0042, 7219.33.0044, 7219.34.0005, 7219.34.0020, 7219.34.0025, 7219.34.0030, 7219.34.0035, 7219.35.0005, 7219.35.0015, 7219.35.0030, 7219.35.0035, 7219.90.0010, 7219.90.0020, 7219.90.0025, 7219.90.0060, 7219.90.0080, 7220.12.1000, 7220.12.5000, 7220.20.1010, 7220.20.1015, 7220.20.1060, 7220.20.1080, 7220.20.6005, 7220.20.6010, 7220.20.6015, 7220.20.6060, 7220.20.6080, 7220.20.7005, 7220.20.7010, 7220.20.7015, 7220.20.7060, 7220.20.7080, 7220.20.8000, 7220.20.9030, 7220.20.9060, 7220.90.0010, 7220.90.0015, 7220.90.0060, and 7220.90.0080. Although the HTS subheadings are provided for convenience and customs purposes, the Department's written description of the merchandise under review is dispositive.

Excluded from the review of this order are the following: (1) Sheet and strip that is not annealed or otherwise heat treated and pickled or otherwise descaled, (2) sheet and strip that is cut to length, (3) plate (*i.e.*, flat-rolled stainless steel products of a thickness of 4.75 mm or more), (4) flat wire (*i.e.*, cold-rolled sections, with a prepared edge, rectangular in shape, of a width of not more than 9.5 mm), and (5) razor blade steel. Razor blade steel is a flat-rolled product of stainless steel, not further worked than cold-rolled (cold-reduced), in coils, of a width of not more than 23 mm and a thickness of 0.266 mm or less, containing, by weight, 12.5 to 14.5 percent chromium, and certified at the time of entry to be used in the manufacture of razor blades. See chapter 72 of the HTS, "Additional U.S. Note" 1(d). Flapper valve steel is also excluded from the scope of the order. This product is defined as stainless steel strip in coils containing, by weight, between 0.37 and 0.43 percent carbon, between 1.15 and 1.35 percent molybdenum, and between 0.20 and 0.80 percent manganese. This steel also contains, by weight, phosphorus of 0.025 percent or less, silicon of between 0.20 and 0.50 percent, and sulfur of 0.020 percent or less. The product is manufactured by means of vacuum arc remelting, with inclusion controls for sulphide of no more than 0.04 percent and for oxide of no more than 0.05 percent. Flapper valve steel has a tensile

strength of between 210 and 300 ksi, yield strength of between 170 and 270 ksi, plus or minus 8 ksi, and a hardness (Hv) of between 460 and 590. Flapper valve steel is most commonly used to produce specialty flapper valves in compressors.

Also excluded is a product referred to as suspension foil, a specialty steel product used in the manufacture of suspension assemblies for computer disk drives. Suspension foil is described as 302/304 grade or 202 grade stainless steel of a thickness between 14 and 127 microns, with a thickness tolerance of plus-or-minus 2.01 microns, and surface glossiness of 200 to 700 percent Gs. Suspension foil must be supplied in coil widths of not more than 407 mm, and with a mass of 225 kg or less. Roll marks may only be visible on one side, with no scratches of measurable depth. The material must exhibit residual stresses of 2 mm maximum deflection, and flatness of 1.6 mm over 685 mm length. Certain stainless steel foil for automotive catalytic converters is also excluded from the scope of this order. This stainless steel strip in coils is a specialty foil with a thickness of between 20 and 110 microns used to produce a metallic substrate with a honeycomb structure for use in automotive catalytic converters. The steel contains, by weight, carbon of no more than 0.030 percent, silicon of no more than 1.0 percent, manganese of no more than 1.0 percent, chromium of between 19 and 22 percent, aluminum of no less than 5.0 percent, phosphorus of no more than 0.045 percent, sulfur of no more than 0.03 percent, lanthanum of less than 0.002 or greater than 0.05 percent, and total rare earth elements of more than 0.06 percent, with the balance iron. Permanent magnet iron-chromium-cobalt alloy stainless strip is also excluded from the scope of this order. This ductile stainless steel strip contains, by weight, 26 to 30 percent chromium, and 7 to 10 percent cobalt, with the remainder of iron, in widths 228.6 mm or less, and a thickness between 0.127 and 1.270 mm. It exhibits magnetic remanence between 9,000 and 12,000 gauss, and a coercivity of between 50 and 300 oersteds. This product is most commonly used in electronic sensors and is currently available under proprietary trade names such as "Arnokrome III."³

Certain electrical resistance alloy steel is also excluded from the scope of this order. This product is defined as a non-magnetic stainless steel manufactured to American Society of Testing and

¹ See Initiation of Five-Year ("Sunset") Reviews, 69 FR 30874 (June 1, 2004) ("Initiation Notice").

² Due to changes to the HTS numbers in 2001, 7219.13.0030, 7219.13.0050, 7219.13.0070, and 7219.13.0080 are now 7219.13.0031, 7219.13.0051, 7219.13.0071, and 7219.13.0081, respectively.

³ "Arnokrome III" is a trademark of the Arnold Engineering Company.

Materials (ASTM) specification B344 and containing, by weight, 36 percent nickel, 18 percent chromium, and 46 percent iron, and is most notable for its resistance to high temperature corrosion. It has a melting point of 1390 degrees Celsius and displays a creep rupture limit of 4 kilograms per square millimeter at 1000 degrees Celsius. This steel is most commonly used in the production of heating ribbons for circuit breakers and industrial furnaces, and in rheostats for railway locomotives. The product is currently available under proprietary trade names such as "Gilphy 36."⁴

Certain martensitic precipitation-hardenable stainless steel is also excluded from the scope of this order. This high-strength, ductile stainless steel product is designated under the Unified Numbering System (UNS) as S45500-grade steel, and contains, by weight, 11 to 13 percent chromium, and 7 to 10 percent nickel. Carbon, manganese, silicon and molybdenum each comprise, by weight, 0.05 percent or less, with phosphorus and sulfur each comprising, by weight, 0.03 percent or less. This steel has copper, niobium, and titanium added to achieve aging, and will exhibit yield strengths as high as 1700 Mpa and ultimate tensile strengths as high as 1750 Mpa after aging, with elongation percentages of 3 percent or less in 50 mm. It is generally provided in thicknesses between 0.635 and 0.787 mm, and in widths of 25.4 mm. This product is most commonly used in the manufacture of television tubes and is currently available under proprietary trade names such as "Durphynox 17."⁵

Finally, three specialty stainless steels typically used in certain industrial blades and surgical and medical instruments are also excluded from the scope of this order. These include stainless steel strip in coils used in the production of textile cutting tools (*e.g.*, carpet knives).⁶ This steel is similar to AISI grade 420 but containing, by weight, 0.5 to 0.7 percent of molybdenum. The steel also contains, by weight, carbon of between 1.0 and 1.1 percent, sulfur of 0.020 percent or less, and includes between 0.20 and 0.30 percent copper and between 0.20 and 0.50 percent cobalt. This steel is sold under proprietary names such as "GIN4 Mo." The second excluded stainless steel strip in coils is similar to AISI 420-J2 and contains, by weight, carbon of between 0.62 and 0.70

percent, silicon of between 0.20 and 0.50 percent, manganese of between 0.45 and 0.80 percent, phosphorus of no more than 0.025 percent and sulfur of no more than 0.020 percent. This steel has a carbide density on average of 100 carbide particles per 100 square microns. An example of this product is "GIN5" steel. The third specialty steel has a chemical composition similar to AISI 420 F, with carbon of between 0.37 and 0.43 percent, molybdenum of between 1.15 and 1.35 percent, but lower manganese of between 0.20 and 0.80 percent, phosphorus of no more than 0.025 percent, silicon of between 0.20 and 0.50 percent, and sulfur of no more than 0.020 percent. This product is supplied with a hardness of more than Hv 500 guaranteed after customer processing, and is supplied as, for example, "GIN6".⁷

Analysis of Comments Received

All issues raised in these reviews are addressed in the "Issues and Decision Memorandum" ("Decision Memo") from Ronald K. Lorentzen, Acting Director, Office of Policy, Import Administration, to James J. Jochum, Assistant Secretary for Import Administration, dated November 15, 2004, which is hereby adopted by this notice. The issues discussed in the Decision Memo include the likelihood of continuation or recurrence of dumping and the magnitude of the margins likely to prevail if the order were to be revoked. Parties can find a complete discussion of all issues raised in this review and the corresponding recommendations in this public memorandum which is on file in room B-099 of the main Commerce Building.

In addition, a complete version of the Decision Memo can be accessed directly on the Web at <http://ia.ita.doc.gov/frn>, under the heading "November 2004." The paper copy and electronic version of the Decision Memo are identical in content.

Final Results of Reviews

We determine that revocation of the antidumping duty order on SSSC from Germany would be likely to lead to continuation or recurrence of dumping at the following percentage weighted-average percentage margins:

Manufacturers/exporters/producers	Weighted average margin (percent)
TKN	13.48
All Others	13.48

⁷ "GIN4 Mo," "GIN5," and "GIN6" are the proprietary grades of Hitachi Metals America, Ltd.

This notice also serves as the only reminder to parties subject to administrative protective orders ("APO") of their responsibility concerning the return or destruction of proprietary information disclosed under APO in accordance with 19 CFR 351.305 of the Department's regulations. Timely notification of the return or destruction of APO materials or conversion to judicial protective order is hereby requested. Failure to comply with the regulations and terms of an APO is a violation which is subject to sanction.

We are issuing and publishing these final results and notice in accordance with sections 751(c), 752, and 777(i)(1) of the Act.

Dated: November 15, 2004.

James J. Jochum,

Assistant Secretary for Import Administration.

[FR Doc. E4-3281 Filed 11-19-04; 8:45 am]

BILLING CODE 3510-DS-P

DEPARTMENT OF COMMERCE

International Trade Administration

[C-580-835]

Stainless Steel Sheet and Strip in Coils From Korea; Extension of Time Limit for the Final Results of Sunset Review of Countervailing Duty Order

AGENCY: Import Administration, International Trade Administration, Department of Commerce.

ACTION: Notice of extension of time limit for the final results of sunset review of countervailing duty order: stainless steel sheet and strip in coils from Korea.

SUMMARY: The Department of Commerce ("the Department") is extending the time limit for its final results in the first sunset review of the countervailing duty order on stainless steel sheet and strip in coils ("SSSS"). The Department intends to issue final results of this sunset review on or about December 10, 2004.

EFFECTIVE DATE: November 22, 2004.

FOR FURTHER INFORMATION CONTACT: Martha Douthit, Import Administration, International Trade Administration, U.S. Department of Commerce, 14th Street and Constitution Avenue, NW., Washington, DC 20230; telephone: (202) 482-5050.

Extension of Final Results of Reviews

On June 1, 2004, the Department initiated a sunset review of the countervailing duty order on SSSS from Korea. *See Initiation of Five-Year*

⁴ "Gilphy 36" is a trademark of Imphy, S.A.

⁵ "Durphynox 17" is a trademark of Imphy, S.A.

⁶ This list of uses is illustrative and provided for descriptive purposes only.